

**Rotary Bauxite RK87**87.0% Min Al₂O₃**PRODUCT DATA**

Property	Specification	Typical
Al ₂ O ₃	87.00% min.	87.5%
TiO ₂	4.00% max.	3.3%
Fe ₂ O ₃	2.00% max.	1.48%
SiO ₂	9.00% max.	7.3%
CaO + MgO	0.50% max.	0.30%
K ₂ O + Na ₂ O	0.30% max.	0.29%

Bulk Density As 3x6 mesh	3.25 g/cc min.	3.32 g/cc
Various Sizes and Packaging Options Available		

Information on this data sheet for general use only and specific situations may apply to all products.
This sheet is property of FX Minerals Pte Ltd. and shall not be used, copied or released without
permission from FX Minerals Pte Ltd.